



Lithium Iron Phosphate Battery Specification

Customer _____

Serial No _____

Part name LiFePO4 Battery

Model No PK-LFP12.8V 6Ah (L90*W70*H101mm)

Approved by		Drafted by	Xiaojun Nie
Checked by		Signed by	Wenfei Liang
Prepared by		Date	2023-11-15

- 1 -

Company address:

9th Floor,Block B,Hongrongyuan North Station Center No. 32, Mintar ing Road,
Longhua District,Shenzhen China.

(Tel) : +86-755-86670672

(Fax) : +86-755-86670609

E-mail: info@batterykcell.com Website: <https://www.batterykcell.com>

1.Scope





This specification is applied to the reference battery in this Specification and manufactured by ShenZhen PKCELL Battery Co., Ltd.

2.Specification

Electrical Characteristics	Nominal Voltage	12.8V
	Nominal Capacity	6Ah@0.5C
	Energy	76.8Wh
	Internal Resistance	≤60mΩ
	Cycle Life	6000 Cycles @ 0.2C 80%DOD
	Charge retention and capacity Recovery capability	Standard charge the battery, and then put aside at room temperature for 28d or 55 °C for 7d, Charge retention rate ≥90%, Recovery rate of charge≥90
Standard Charging	Max.Charging Voltage	14.2-14.6V
	Charging Mode	0.2C to 14.6V, then 14.6V,charge current to 0.02C (CC/CV)
	Charging Current	1.2A
	Max.Charging Current	3A
Standard Discharging	Discharging Current	1.2A
	Max. Continuous Current	3A
	Max.Pulse Current	6A(<1.5S)
	Discharging Cut-off Voltage	10.0V
Operating Condition	Charge Temperature	0°C to 45°C(32°F to 113°F) @60±25% Relative Humidity
	Discharge Temperature	-20°C to 60°C(-4°F to 140°F) @60±25% Relative Humidity
	Storage Temperature	0°C to 45°C(32°F to 113°F) @60±25% Relative Humidity
	Water Dust Resistance	IP55
	Casing	Plastic
	Dimension(L*W*H)	90*70*101mm
	Weight	Approx: 0.66Kg
Terminal	F2	

- 3 -

3. Discharge performance graph



4 -

4. Safe Characteristic

No.	Item	Testing Instruction	Requirement
1	Over-charge test	Charge in accordance with the following two ways (Choosing one between the two). (1) Charge at 1C current for 90 min or until voltage of some single battery reaches 5.0 V (stop test when fulfills either condition). (2) Charge at 3C current until the voltage of some single battery reaches 10.0 V, then stop the test.	The battery shall not explode or catch fire
2	Over- discharge test	Charge the battery. Place at 20±5°C for 1h, then discharge in 1/3 C current at same emperature until some cell's voltage is 0V	The battery shall not explode or catch fire
3	Short- ircuiting Test	After charge batteries, place at 20±5°C for 1h. Short the battery for 10 min, the external circuit resistance should be less than 5mΩ.	The battery shall not explode or catch fire

5. Environmental Characteristic

No.	Item	Testing Instruction	Requirement
1	Vibration Test	The battery will be vibrated 30 minutes in three mutually perpendicular directions and changing frequency between 10 to 55Hz. The rate of scanning frequency is from 10 Hz to 55Hz with the rate of 1Hz per min. Vibration frequency: 10-30Hz amplitude: 0.38mm vibration frequency: 30-55Hz: amplitude: 0.19mm	The battery shall not rupture, smoke, explode or leak. Battery electric voltage 12.8V
2	Constant Temperature/ Humidity Test	Keep the battery at $40\pm 2^{\circ}\text{C}$ and 90%-95%RH for 48 hrs after complete charge. After the test, keep the battery at $20\pm 5^{\circ}\text{C}$ for 2 hrs. Discharge at 10A constant current discharge to the termination voltage.	Appearance of the battery shall not rust, smoke or explode. Discharge Capacity $\geq 80\%$
3	High Temperature Performance Test	Keep the battery at a hot oven with $55\pm 2^{\circ}\text{C}$ for 2 hrs, then measure the capacity with constant discharge current 0.5C to discharge protection point after complete charge. After the test, keep the battery at $20\pm 5^{\circ}\text{C}$ for 2 hrs.	Appearance of the battery shall not rust, smoke or explode Discharge Capacity $>90\%$
4	Low Temperature Performance Test	Keep the battery at $-20\pm 2^{\circ}\text{C}$ for 20 hrs, then measure the capacity with constant discharge current 0.5C to discharge protection point after complete charge. After the test, keep the battery at $20\pm 5^{\circ}\text{C}$ for 2 hrs.	Appearance of the battery shall not rust, smoke or explode Discharge Capacity $>55\%$

- 5 -

6. Storage conditions

When the battery pack to be long-term stored, charge the battery pack to about 60% capacity, store in dry and ventilated place, Charge it every 3 months.

The battery pack and charger should be stored in clean, dry and ventilated place, avoid contacting with corrosive materials and be away from fire and heat.

7. Battery Handling Precautions

Don't disassemble the battery.

Don't discard the battery in fire or heater.

Don't connect the positive and negative terminal directly with metal objects.

Don't immerse the battery in water.


Don't use of damaged battery.

Don't connect the battery to an electrical outlet directly

When charging, use a battery charger specifically for that purpose.

The battery replacement shall be done only by either cells supplier or device supplier and never be done by the user.

8. Dimension




- 6 -



8.Wrap

(For reference only)



- 7 -

.....END.....